

[オーステナイト系ステンレス鋼]

下村 鋼種記号	化学成分 (wt%)									
	C	Si	Mn	P	S	Cu	Ni	Cr	Mo	他
SF30V	≦0.15	≦1.00	≦2.00	≦0.20	≧0.15	—	9.50 - 10.00	17.00 - 19.00	≦0.60	—
SF27E	≦0.15	≦1.00	≦2.50	≦0.20	≧0.15	2.50 - 3.50	8.00 - 10.00	17.00 - 19.00	≦0.60	—
SUS303	≦0.15	≦1.00	≦2.00	≦0.20	≧0.15	—	8.00 - 10.00	17.00 - 19.00	≦0.60	—
DSH400F	≦0.08	≦1.00	≦2.00	≦0.20	≧0.15	—	8.00 - 10.00	17.00 - 19.00	添加	特殊元素 添加
SUS304	≦0.08	≦1.00	≦2.00	≦0.045	≦0.030	—	8.00 - 10.50	18.00 - 20.00	—	—
SUS304N2	≦0.08	≦1.00	≦2.50	≦0.045	≦0.030	—	7.50 - 10.50	18.00 - 20.00	N 0.15- 0.30 Nb≦0.15	—
SUS316	≦0.08	≦1.00	≦2.00	≦0.045	≦0.030	—	10.00 - 14.00	16.00 - 18.00	2.00 - 3.00	—
SUS310S	≦0.08	≦1.50	≦2.00	≦0.045	≦0.030	—	19.00 - 22.00	24.00 - 26.00	—	—
SUH660	≦0.08	≦1.00	≦2.00	Ti 1.90 - 2.35	B 0.001 - 0.010	—	24.00 - 27.00	13.50 - 16.00	1.00 - 1.50	V0.10-0.50 Al≦0.35